



**COPELAND COATING
COMPANY, INC.**



ACTION-PAVE®
ATHLETIC SURFACES

ACTION PAVE ACRYLIC FILLER COAT(S)

DESCRIPTION -

100% acrylic emulsion, special reinforcing pigments and pure silica sand that provides a uniform and controlled texture which is extremely durable, however, remains flexible. ACTION PAVE ACRYLIC FILLER COAT(S) has been specifically engineered to protect asphalt and concrete surfaces from the harsh northeast weather conditions. Unlike other acrylic surfacing fillers, ACTION PAVE ACRYLIC FILLER is fully pigmented, resulting in longer lasting, richer, full depth color.

USE -

Apply over existing color coated surfaces to rejuvenate and add texture. The ACTION-PAVE ACRYLIC FILLER coat(s) can be tailored to increase or decrease the speed of the surface. Apply over new surfaces which have had the ACTION PAVE ACRYLIC RESURFACER properly applied and cured.

APPLICATION -

Use a standard, commercial quality, squeegee 24", 30" or 36" in width. Clean squeegee with water immediately after use.

MIX DESIGN -

ACTION PAVE ACRYLIC FILLER is concentrated and needs to be mixed on site with clean water. Thorough mixing is required. Mortar mixer offers best results.

2 parts ACTION PAVE ACRYLIC FILLER
1 part water

COVERAGE -

To surface the standard tennis court (800 square yards) a one (1) coat application will require 60 gallons of concentrated ACTION PAVE ACRYLIC FILLER. A two (2) coat application will require 115 gallons of concentrated ACTION PAVE ACRYLIC FILLER. A three (3) coat application will require 165 gallons of concentrated ACTION PAVE ACRYLIC FILLER. Approximate coverage ratio for a standard two (2) coat application = 7 square yards per gallon of concentrate.

SURFACE PREPARATION AND APPLICATION -

The surface must be clean and free of grease, oil and any other foreign material. ACTION PAVE ACRYLIC FILLER coat is to be applied over previously color coated surfaces or new surfaces which have already had ACTION PAVE ACRYLIC RESURFACER applied. All crack repair and other preparation must be completed.

Spread ACTION PAVE ACRYLIC FILLER coat evenly by walking in one direction and then reversing direction. Always maintain a wet edge and do not overwork the material. Avoid leaving any puddles when squeegeeing material back and forth. Before applying the next filler coat, or the final finish coat, allow coating to dry sufficiently and inspect it. Scrape off any ridges, lumps or other imperfections and then apply the next coat.

Page 1 of 2

3600 US Route 20
PO Box 595
Nassau, (Albany area) NY 12123
www.copelandcoating.com



(518) 766-2932
(800) 303-4219
Fax: (518) 766-3603
E-mail: ActionPave@copelandcoating.com

"The pavement maintenance people...since 1945"



LIMITATIONS -

- Do not apply ACTION PAVE ACRYLIC FILLER coat(s) when surface temperature is below 50°F (10°C) or when fog, rain or high humidity is imminent.
- Do not apply if surface temperature is above 130°F (55°C).
- Do not store in direct sunlight.
- Close cover tightly.
- Keep from freezing.