



**COPELAND COATING
COMPANY, INC.**



ACTION-PAVE®
ATHLETIC SURFACES

ACTION PAVE® ACRYLIC RESURFACER

DESCRIPTION -

ACTION PAVE ACRYLIC RESURFACER (concentrated acrylic resurfacing emulsion) is a heavy bodied, 100% acrylic emulsion developed specifically for use on open or pitted asphalt surfaces to reduce porosity and provide a uniform surface texture. Application of ACTION PAVE ACRYLIC RESURFACER provides an economical means for filling voids in asphalt pavements and protecting the asphalt from ultra-violet rays.

USE -

Apply over newly paved surfaces or old, severely oxidized, pitted surfaces.

APPLICATION -

Use a standard, commercial quality, squeegee 24", 30" or 36" in width, or spray apply product. Clean squeegee or sprayer with water immediately after use.

MIX DESIGN -

ACTION PAVE ACRYLIC RESURFACER is concentrated and needs to be mixed on site with clean water. Thorough mixing is required. Mortar mixer offers best results.

2 parts ACTION PAVE ACRYLIC RESURFACER
1 part water

COVERAGE -

The amount of material needed will vary slightly due to variation in density of the asphalt substrate and the technique of application. Approximate coverage ratio = twelve (12) square yards per gallon of concentrate.

SURFACE PREPARATION AND APPLICATION -

The surface must be clean and free of grease, oil and any other foreign material. New asphalt shall cure a minimum of five (5) days and may require a longer curing period in cold or dry climate areas. Pour a ribbon of material along one end of the area to be surfaced. Spread evenly by walking in one direction and then reversing direction or spray product in same manner. Always maintain a wet edge and do not overwork material. Before applying the next coat of material, inspect coating and scrape off any ridges, lumps or other imperfections and then apply the next coat 90° to this coat.

LIMITATIONS -

- Do not apply ACTION PAVE ACRYLIC RESURFACER when surface temperature is below 50°F (10°C) or when fog, rain or high humidity is imminent.
- Do not apply if surface temperature is above 130°F (55°C).
- Do not store in direct sunlight.
- Close cover tightly.
- Keep from freezing.

3600 US Route 20
PO Box 595
Nassau, (Albany area) NY 12123
www.copelandcoating.com



(518) 766-2932
(800) 303-4219
Fax: (518) 766-3603
E-mail: ActionPave@copelandcoating.com

"The pavement maintenance people...since 1945"