


Action-Track® 100

Resilient Urethane Track Surface



T E C H N I C A L D A T A

1. Purpose:

The intent of this specification is to provide a guideline for the improvement of a previously sound bituminous concrete sub-base. Action Track 100 is a mixture of uniformly graded black EPDM rubber granules bound with 100% polyurethane binder. This system is a pervious all weather surface extremely durable, resilient and self-sealing.

2. Scope:

The work covered by this specification consists of furnishing all labor, equipment, materials and performance of all operations in connection with the installation of the surface on track and field events.

3. Materials:

- Action Track Polyurethane Primer
- EPDM Rubber Base Mat Granulate, 1 mm to 3mm or 1 mm to 4mm rubber containing no dust.
- Clear, 100% polyurethane base mat binding agent.
- Polyurethane line marking paint.

4. Surface Preparation:

- After a suitable soil sterilant, a recommended bottom course shall consist of 4" to 8" of compacted crushed stone, gravel, or suitable aggregate over a firm, stable frost-free sub-grade which has been brought to proper contour and elevation in strict accordance with drawings and/or specifications, and compacted to 95% density.
- A binder-leveling course of an open-textured bituminous concrete (maximum stone size of 3/4") is laid upon the prepared bottom course to a compacted thickness of 1.5".
- The wearing (top) bituminous concrete course consists of 3/8" maximum aggregate to a thickness of 1" compacted.

5. Planarity and Slope:

Before the application of the surface course, the asphalt base should be tested for planarity using a 10' straight edge. All leveling work should be performed so that the finished surface slope is a minimum of 1%. Low spots to be rectified prior to installation of base mat.

6. Procedure:

- Following inspection of asphalt base and required curing time, the entire area to be surfaced shall be thoroughly cleaned, removing any foreign and loose material.
- Action Track Polyurethane Primer will then be applied to the entire surface uniformly at a rate of not less than .3 lbs. per sq. yd. Allowing a minimum of 30 minutes curing time before the application of the base mat material.
- The base mat will consist of an 18 to 23% range polyurethane base mat binding agent and 77 to 82% range EPDM rubber base mat granulate as described above. This mixture is prepared in a mechanical mixer which is clean and dry. The base mat is applied with a mechanically operated screed machine which has an electrically heated screed. Joint work will be flush with the adjacent mat. Joints which have cured will have their edges primed with Action Track Polyurethane Primer.

7. Minimum Physical Properties Of The Surface:

- THICKNESS: 1/2" or as specified by architect or engineer
- HARDNESS: (ASTM D2240): Shore A @ 70°F - 50 to 60, @ 140°F - 45 to 55, @ 35°F - 55 to 65
- ELONGATION (ASTM D412): 95%
- TENSILE STRENGTH (ASTM D412): 200 psi @ 70°F over a 24 hour period
- ABRASION RESISTANCE (ASTM D501): 0.25 TO 0.425 grams' loss after 1000 cycles
- CHALKING (ASTM D822): No change after 1000 hours in weatherometer
- COEFFICIENT OF FRICTION (ASTM D1 894): Dry- 0.70 to 0.75 • Wet- 0.80 to 0.95
- RESILIENCE (ASTM D2632): 37 TO 44%
- TEAR RESISTANCE ASTM D624): 50 TO 75 PSI-

8. LINE MARKINGS:

The measurements and markings of the lines and events will be performed according to the recommendations of Copeland Coating Company, Inc. and/or in accordance with IAAF, NCAA regulations and NFHSA. The line paint used shall be compatible with polyurethane surface as recommended by Copeland Coating Company, Inc.

9. Colors Available: Black

COPELAND COATING COMPANY

"THE PAVEMENT MAINTENANCE PEOPLE SINCE... 1945"

P.O. Box 595, Nassau, NY 12123 (Albany Area) (518) 766-2932

www.copelandcoating.com

